

LUSTRE/METALLIC (L) LOW FIRE GLAZES

GLAZES



NON-TOXIC
Conforms to
ASTM D-4236



L-512 (4)
Lustre Brown



L-514 (4)
Midnight Blue



L-516 (4)
Sparkling Burgundy

CL GLAZES RESTRICTED FROM USE K-6 (ASTM D-4236/FHSA)



Conforms to
ASTM D-4236



L-511 (4)
Lustre Green



L-518 (3)
Lustre Gold



L-520 (3)
Bronze Patina

NEW!

*L Series glazes fired on 25M
White Clay bisque buttons.*

Standard Shipping Units: 12 (4 oz., 16 oz., 1 lb.) and 4 (Gallons).

AMACO® Lustre and Metallic Glazes

CL colors are restricted from use K-6 (ASTM/FHSA). All L Series glazes are lead free except L-518 and L-520.

Cone 06-05. These glazes provide the metallic look of hard steel and the high brilliance of lustre. The end result is determined by the structure of the ware and the method of application. Lustre and Metallic glazes can be used in conjunction with other glazes or by themselves. The Lustre and Metallic glazes can be

high fired to Cone 4-6 (2161°-2269°F, 1183°-1243°C) with fantastic results.

Stir and mix Lustre and Metallic glazes thoroughly. They should be the consistency of rich cream. If thinning is necessary, add a little water and AMACO® Gum Solution. Apply these glazes by brushing or sponging on a mature Cone 04 (1971°F, 1077°C) bisque. Fire to Cone 06-05 (1855°-1911°F, 1013°-1044°C). L-518 only: fire to Cone 04 (1971°F, 1077°C).

Lustre and Metallic Glazes



Series No.	Color	4 fl. oz. Cat. No.	Pint Liquid Cat. No.
*L-512...	Lustre Brown (4) [SO]	38701B	
*L-514 ..	Midnight Blue (4) [ST]	38702C	
*L-516 ..	Sparkling Burgundy (4) [SO]	38703D	

CL GLAZES RESTRICTED FROM USE K-6 (ASTM D-4236/FHSA)



L-511 ..	Lustre Green (4) [ST]	38700A	
L-518 ..	Lustre Gold (3) [O]	38704E	60784S
L-520 ..	Bronze Patina (3) [SO]	38705F	38706H

[ST] = Semi-translucent [SO] = Semi-opaque
Only glazes marked with an asterisk () may be used for safe spray application.

NEW!